

## Conformal Coatings

# Dow Corning® 3-1944 RTV Coating

### FEATURES

---

- Flowable
- Compliant to most international regulations
- Room temp cure with optional heat acceleration
- Cures to soft, low stress elastomer
- UL 746 and Mil Spec tested
- IPC-CC-830
- UV indicator for inspection
- No added solvents

### BENEFITS

---

- No mixing required
- RT cure, no ovens required
- Faster in-line processing with optional heat acceleration
- Able to flow, fill or self-leveling after dispensing
- UV indicator allows for automated inspection
- Good adhesion allows use with many low-solids (no clean) and no-lead solders
- Can be considered for uses with UL, IPC or Mil Spec requirements

### COMPOSITION

---

- 1-part, translucent
- Polydimethylsiloxane coating

### APPLICATION METHODS

---

- Brush
- Flow Coating
- Syringe or needle

**Coating or adhesive with added UV indicator, good flowability, fast tack free time, good flame resistance, MIL A-46058 tested**

### APPLICATIONS

- Pin/solder joint coverage
- Thin section encapsulation
- Spot protection of pins or other devices

### TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Property	Unit	Value
Viscosity	cP	63775
	mPa-sec	63775
	Pa-sec	63.8
Specific Gravity (Cured)	-	1.03
Tack-Free Time at 25°C	minutes	14
Durometer Shore A	-	36
Tack-Free Time at 60°C/15% RH	minutes	0.5
Tensile Strength	psi	325
	MPa	2.2
	kg/cm2	22
Elongation	%	145
Youngs Modulus	psi	223
	MPa	1.54
	kg/cm2	15.4
Unprimed Adhesion - 180 Degree Peel Strength	ppi	5
	N/cm	3
Dielectric Strength	volts/mil	525
	kV/mm	21
Volume Resistivity	ohm*cm	1.6 E15
Shelf Life at 25°C	months	12

---

## TYPICAL PROPERTIES, continued

### DESCRIPTION

Solventless RTV elastomeric conformal coatings require atmospheric moisture to cure needing no expensive ovens, and various viscosity version facilitate different application methods. This family of coatings is rapidly gaining popularity due to its environmentally friendly and solventless formulations, its rapid cure rates that can be dramatically accelerated by mild heat, and its cost effectiveness. These elastomers, when cured, offer the optimum stress relief for even the most delicate components and interconnections in a variety of service environments. This product line also features coatings manufactured for controlled volatility and many of these products are UL recognized. Conformal coatings are materials applied in thin layers (typically a few mils or microns) onto printed circuits or other electronic substrates. They provide proven, cost effective environmental and mechanical protection to significantly extend the life of the components and circuitry. Underwriters Laboratory (UL) 746E recognition is based on thickness and substrate requirements. Please consult the UL Online Certifications Directory for the most accurate certification information.

### PROCESSING/CURING

Time to cure is dependent on several variables including the method of application, film thickness, temperature and humidity. Tack-free time in the data table gives an indication of typical times until surface is dry enough to handle. Cure time for full cure are indications of time needed to develop full physical properties such as durometer, tensile strength or adhesion. These times, including full cure time, can be significantly improved by introducing mild heat of 60°C or less.

### POT LIFE AND CURE RATE

The pot life of Dow Corning RTV Conformal Coatings is dependent on the application method chosen. To extend pot life, minimize exposure to moisture by using dry air or dry

Property	Unit	Value
UL Flammability Classification	NA	94 V-0
Mil Specification	NA	Mil I-46058C Amend 7
Agency Listing	-	IPC-CC-830B, UL 746E

nitrogen blanketing whenever possible.

### ADHESION

With RTV cure coatings, adhesion typically lags behind cure and may take 72 hours to build in some coatings. Dow Corning Conformal Coatings are formulated to provide adhesion to most common electronic substrates and materials. On certain difficult, low-surface energy surfaces, adhesion may be improved by priming or by special surface treatment such as chemical or plasma etching.

### USABLE LIFE AND STORAGE

Special precautions must be taken to prevent moisture from contacting Dow Corning RTV Conformal Coatings. Containers should be kept tightly closed and head or air space minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. Shelf life is indicated by the "Use Before" date found on the product label.

### USEFUL TEMPERATURE RANGES

For most uses, silicone elastomers should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but

performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

### REPAIRABILITY

In the manufacture of electronic devices, it is often desirable to salvage or reclaim damaged or defective units. Dow Corning Conformal Coatings offer excellent repairability because they can be removed from substrates and circuitry by scraping or cutting, or by using solvents or stripping agents. If only one circuit component is to be replaced, a soldering iron may be applied directly through the coating to remove the component. After the circuit board has been repaired, the area should be cleaned by brushing or by using solvent, then dried and recoated. Heat cure coatings can be repaired with RTV coatings, but heat cure coatings may not work well when used to repair RTV coatings.

### PACKAGING

In general, Dow Corning Conformal Coatings are supplied in nominal 0.45-, 3.6-, 18- and 200-kg (1-, 8-, 40- and 440-lb) containers, net weight. Not all coatings may be available in all packages and some additional packages, such as bladder packs or tubes, may be available for certain coatings and package sizes.

**HANDLING  
PRECAUTIONS  
PRODUCT SAFETY  
INFORMATION REQUIRED  
FOR SAFE USE IS NOT  
INCLUDED IN THIS  
DOCUMENT. BEFORE  
HANDLING, READ PRODUCT  
AND MATERIAL SAFETY DATA  
SHEETS AND CONTAINER  
LABELS FOR SAFE USE,  
PHYSICAL AND HEALTH  
HAZARD INFORMATION. THE  
MATERIAL SAFETY DATA  
SHEET IS AVAILABLE ON THE  
DOW CORNING WEBSITE AT  
WWW.DOWCORNING.COM, OR  
FROM YOUR DOW CORNING  
REPRESENTATIVE, OR  
DISTRIBUTOR, OR BY  
CALLING YOUR GLOBAL DOW  
CORNING CONNECTION.**

**HEALTH AND  
ENVIRONMENTAL  
INFORMATION**

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each

area. For further information, please see our website, [www.dowcorning.com](http://www.dowcorning.com) or consult your local Dow Corning representative.

**LIMITATIONS**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**LIMITED WARRANTY  
INFORMATION PLEASE  
READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent. Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or

replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY  
DISCLAIMS ANY OTHER  
EXPRESS OR IMPLIED  
WARRANTY OF FITNESS FOR  
A PARTICULAR PURPOSE OR  
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS  
LIABILITY FOR ANY  
INCIDENTAL OR  
CONSEQUENTIAL DAMAGES.**

*We help you invent the future.™*

**[dowcorning.com](http://dowcorning.com)**